

Glass fiber surface mat

Product Code	Area Weight (g/m ²)	Stregth(N/50mm)		Glue Content(%)	Thickness (mm)	Moisture Content(%)
		Warp	Weft			
S-HM10	10±1	≥10	≥8	5~15	0.10±0.02	≤0.2
S-HM20	20±1	≥30	≥25	5~15	0.16±0.03	≤0.2
S-HM30	30±1.5	≥50	≥40	5~15	0.24±0.03	≤0.2
S-HM50	50±2	≥80	≥65	5~15	0.43±0.05	≤0.2
S-HM100	100±5	≥120	≥90	7~20	0.90±0.05	≤0.2
S-HM200	200±10	≥240	≥180	10~25	1.70±0.10	≤0.2
S-HM300	300±15	≥360	≥280	10~25	2.60±0.20	≤0.2
S-HM450	450±20	≥450	≥360	10~25	3.80±0.30	≤0.2